

PRODUCT SPECIFICATIONS

BPD-800

Description: HDI/Trimethylol Hexyllactone Crosspolymer (And) Silica

Test ID	Test Name	Specification	Test Methods
001A	Appearance	White to pale yellow powder	Visual
002A	Odor	Odorless	Organoleptic
010A	Loss on Drying, %	Min : 0 - Max : 3	2hrs. @ 105°C
012B	Microbiology	<100 cfu/g; No Pathogens	Current USP Microbial Limit Test
017B	Loss on Ignition, %	Min : 94	3hrs. @ 500°C
024C	Average Particle Size, µm	Min : 5.50 - Max : 8.00	Coulter Counter
024J	Particle Size Range, µm	5.5 to 10.2µm more than 70%	Light Scattering Sizer
025I	pH 10% Aq. Dispersion	Min : 5.50 - Max : 7.50	10% slurry, measure supernant
027A	Arsenic, ppm	Min : 0 - Max : 2	JSCI Method
029F	Lead, ppm	Min : 0 - Max : 10	JSCI Method

If you have any questions about the information contained within this document, please contact Kobo's QC department extension 7113 or 7106.

Nov. 2010