

PRODUCT SPECIFICATIONS

RBTD-MS3

INCI Name: Titanium Dioxide (And) Methicone (And) Alumina

Test ID	Test Name	Specification	Test Methods
001A	Appearance	White Powder, Tms	Visual
002A	Odor	Characteristic, Tms	Organoleptic
010B	Loss on Drying, %	Min : 0 - Max : 1	15 min at 80 C
012B	Microbiology	<100 cfu/g; No Pathogens	Current USP Microbial Limit Test
027G	Arsenic, ppm	Min : 0 - Max : 1	CTFA Method F 1-1, Silver Diethyldithiocarbamate
029B	Lead, (as Pb), ppm	Min : 0 - Max : 10	Weak Acid Extraction AA Method
031C	Mercury, ppm	Min : 0 - Max : 1	AAS
033A	Hydrophobicity	Place 5g On 45g water. Shake 10 times. Water remains clear.	Shake powder with water in a jar
038A	Apparent Density, gm/cbi		CTFA Method C8-2, Scott Volumeter
998A	* Note	TiO2 prior to surface treatment meets all CFR requirements and passes USP specifications.	

If you have any questions about the information contained within this document, please contact Kobo's QC department extension 7113 or 7106.
Aug. 2010