

# Anhydrous Crème-to-Powder Concealer featuring Formula KCP-018

## ITT-Treated Pigments

Kobo Products - formulations

Part	Percent	Ingredients	INCI Name	Supplier
<b>1</b>	15.00	<b>ASO-I2</b>	Aluminum Starch Octenylsuccinate (And) Isopropyl Titanium Triisostearate	<b>Kobo Products</b>
	12.99	<b>BTD-401</b>	Titanium Dioxide (And) Isopropyl Titanium Triisostearate	<b>Kobo Products</b>
	6.25	<b>SERICITE GMS-4C</b>	Mica	<b>Kobo Products</b>
	2.00	<b>MSS-500/3</b>	Silica	<b>Kobo Products</b>
	0.33	<b>BRO-I2</b>	Iron Oxides (C.I. 77491) (And) Isopropyl Titanium Triisostearate	<b>Kobo Products</b>
	0.33	<b>BYO-I2</b>	Iron Oxides (C.I. 77492) (And) Isopropyl Titanium Triisostearate	<b>Kobo Products</b>
	0.10	<b>BBO-I2</b>	Iron Oxides (C.I. 77499) (And) Isopropyl Titanium Triisostearate	<b>Kobo Products</b>
<b>2</b>	18.00	Liponate® EHP	Ethyl Hexyl Palmitate	Lipo Chemicals
	11.00	<b>Element14 PDMS 5</b>	Dimethicone	<b>Momentive/Kobo Products</b>
	6.50	Squalane NF	Squalane	Barnet Products Corp.
	5.50	Lameform® TGI	Polyglycerol-3 Diisostearate	Cognis Corp.
	4.00	Microcrystalline Wax SP-89	Microcrystalline Wax	Strahl & Pitsch, Inc.
	3.00	Mineral Oil Carnation	Mineral Oil	Ruger Chemical Co., Inc.
	2.00	Softisan® 100	Hydrogenated Coco-Glycerides	Sasol
	1.00	Carnauba Wax SP 63P	Copernicia Cerifera (Carnauba) Wax	Strahl & Pitsch, Inc.
<b>3</b>	12.00	<b>SP-500</b>	Nylon-12	<b>Toray/Kobo Products</b>

100

### Manufacturing Procedure

1. Micronize Part 1 until the color is fully developed.
2. Heat Part 2 with stirring to 90°C.
3. Continue to stir and maintain temperature for 30 minutes.
4. Add Part 1 to Part 2 and mix until homogeneous.
5. Cool to 80°C and add Part 3.
6. Pour into pans at 75°C.

### Description

This crème-to-powder concealer covers imperfections and immediately gives a powder base so foundation can be applied over it. Kobo's BTD-401 gives high coverage. A combination of Kobo's Sericite and ITT-Treated starch and pigments provides the basis for the crème-to-powder texture. A combination of Kobo's Microspheres, MSS-500/3 and SP-500, gives a glide-on application and helps to provide soft focus.

### **Kobo Products, Inc.**

3474 South Clinton Avenue, South Plainfield, NJ 07080 - USA  
tel: +1 - 908-757-0033 fax: +1 - 908-757-0905 info@koboproductsinc.com

December, 2010

# **KOBO**

www.koboproducts.com

## Formulations

Product formulations are included as illustrative examples only. Kobo Products Inc. makes no representation or warranty concerning the efficacy or safety of any product manufactured using such formulations. All statements concerning the possible use of Kobo Products Inc. are for research purposes only. Responsibility for the performance or adequate testing of any product prior to sale or use of any such product lies with the manufacturer thereof.

## Use of Products

Products sold by Kobo are designed, manufactured and sold for industrial use only. Prior to use of any such product for any application other than an industrial use, the user has the sole responsibility and obligation to determine the suitability of any such product for any such application.

## Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

## Limitation of Liability

Kobo Products Inc. shall in no event, whether the claim is based on warranty, contract, tort, strict liability, negligence or otherwise, be liable for incidental or consequential damages, or for any other damages in excess of the amount of the purchase price.

# The Powder & Dispersion Specialist

**KOBO**  
[www.koboproducts.com](http://www.koboproducts.com)

***Kobo Products, Inc.***

3474 South Clinton Avenue  
South Plainfield, NJ 07080 - USA  
tel : +1 - 908-757-0033  
fax : +1 - 908-757-0905

***Kobo Products SAS***

Rue Buissonnière. BP 67660  
31676 Labege Cedex - FRANCE  
tel : +33 - (0)5-62-88-77-40  
fax : +33 - (0)5-62-88-77-49