

PRODUCT SPECIFICATIONS

WSJ28PFAMP

INCI Name: Water (And) Acrylates/Ethylhexyl Acrylate Copolymer (And) Titanium Dioxide (And) Sodium Acrylate/Sodium Acryloyldimethyl Taurate Copolymer (And) Alumina (And) Aminomethyl Propanol

Test ID	Test Name	Specification	Test Methods
001A	Appearance	White viscosus liquid, TMS	Visual
002A	Odor	Characteristic, TMS	Organoleptic
010A	Loss on Drying, %	Min : 42 - Max : 46	2hrs. @ 105°C
012B	Microbiology	<100 cfu/g; No Pathogens	Current USP Microbial Limit Test
021D	Residual Monomer, ppm	<50 ppm	JSCI Method
025I	pH 10% Aq. Dispersion	Min : 6.50 - Max : 8.50	10% slurry, measure supernant
027G	Arsenic, ppm	Min : 0 - Max : 3	CTFA Method F 1-1, Silver Diethyldithiocarbamate
029B	Lead, (as Pb), ppm	Min : 0 - Max : 10	Weak Acid Extraction AA Method
031C	Mercury, ppm	Min : 0 - Max : 1	AAS
036A	Identification	To match standard	IR
042B	Residue on Ignition, %	Min : 26.00 - Max : 29.50	3hrs. @ 500°C

If you have any questions about the information contained within this document, please contact Kobo's QC department extension 7113 or 7106.

Aug. 2010