

Silane Treatment




INCI Name: Triethoxycaprylsilane

Code: Treatment 11S

Triethoxycaprylsilane is a very reactive surface-treating agent, because the hydrolysis of Si-O bond takes place readily in presence of moisture to form silanol.

The caprylsilyl group is then chemically bonded to the pigment via a condensation reaction between the silanol group formed above and the hydroxyl groups of the pigment surface. This reaction is thus especially suitable for treatment of metal oxides. At the completion of the reaction, all ethoxy groups are substituted and caprylsilyl groups are crosslinked to the pigments to form a very stable coating, even at low pH.

Silicone treated pigments disperse well in cyclomethicones. They have a very low surface tension and excellent hydrophobicity, but they sometimes have poor wettability in common organic vehicles.



While they offer maximum water repellency, triethoxycaprylsilane treated pigments, because of the lipophilic capryl groups, are easy to disperse in esters, hydrocarbons and silicone fluids : higher pigment loading can be achieved as compared to methicone treated pigments.

The treatment is also physicochemically stable, even at pH 3, has no residual methanol, and, due to the absence of Si-H bonds, has zero hydrogen potential.

Trade Name	INCI Name	Product type
BRO-11S2	Iron Oxides (CI 77491) (And) Triethoxycaprylsilane	Red Iron Oxide
BYO-11S2	Iron Oxides (CI 77492) (And) Triethoxycaprylsilane	Yellow Iron Oxide
BBO-11S2	Iron Oxides (CI 77499) (And) Triethoxycaprylsilane	Black Iron Oxide
BLACK NF-11S2		
BGCO-11S3	Chromium Oxide Greens (And) Triethoxycaprylsilane	Green Chromium
BHG TM-11S2	Chromium Hydroxide Greens (And) Triethoxycaprylsilane	Green Chromium Hydroxide
BFF-11S2	Ferric Ammonium Ferrocyanide (And) Triethoxycaprylsilane	Blue Ferric Amm. Ferrocyanide
BEUB-11S2		Ultramarine Blue
New BUP-11S2	Ultramarines (And) Triethoxycaprylsilane	Ultramarine Pink
BUV CG-11S2		Ultramarine Violet
BTD-11S2		
RBTD-671-11S2	Titanium Dioxide (And) Triethoxycaprylsilane	Pigmentary TiO ₂

KOBO

USA - New Jersey
+1 (908) 757-0033

BRASIL - São Paulo
+55 (11) 5062-0634

UK- Abingdon
+44 7913 636 673

FRANCE - Labege
+33 (0)5-62-88-77-40

Trade Name	INCI Name	Product type
BLUE 1AL-11S4	Blue 1 Lake (And) Triethoxycaprylylsilane	FD&C Blue No. 1 Aluminum Lake
RED 6BA C-11S5	Red 6 Lake (And) Triethoxycaprylylsilane	D&C Red No. 6 Barium Lake
RED 7CA C-11S5	Red 7 Lake (And) Triethoxycaprylylsilane	D&C Red No. 7 Calcium Lake
RED 27AL-11S3	Red 27 Lake (And) Triethoxycaprylylsilane	D&C Red No. 27 Aluminum Lake
RED 28AL C-11S3	Red 28 Lake (CI 45410) (And) Triethoxycaprylylsilane	D&C Red No. 28 Aluminum Lake
RED 33AL-11S2	Red 33 Lake (And) Triethoxycaprylylsilane	D&C Red No. 33 Aluminum Lake
YELLOW 5AL-11S2	Yellow 5 Lake (And) Triethoxycaprylylsilane	FD&C Yellow No. 5 Aluminum Lake
YELLOW 6AL-11S2	Yellow 6 Lake (And) Triethoxycaprylylsilane	FD&C Yellow No. 6 Aluminum Lake
RED 6SS-11S2	Red 6 (And) Triethoxycaprylylsilane	D&C Red No. 6
GMS-11S2		Sericite
MICA S-11S4	Mica (And) Triethoxycaprylylsilane	Mica
New KoboMica 1000S-11S2	Synthetic Fluorophlogopite (And) Triethoxycaprylylsilane	Synthetic Fluorophlogopite
TALC U-11S2	Talc (And) Triethoxycaprylylsilane	Talc
ASO-11S2	Aluminum Starch Octenylsuccinate (And) Triethoxycaprylylsilane	Aluminum Starch Octenylsuccinate
MT-600B-11S5	Titanium Dioxide (And) Triethoxycaprylylsilane	UV-Attenuation TiO ₂
A120-ZNO-11S3		
MZO-35-11S5		
New ZnO-660SS-11S5	Zinc Oxide (And) Triethoxycaprylylsilane	UV-Attenuation ZnO
ZNO FSF-11S4		
New ZNO XZ-11S3L		
New A1K-TiO2-11S2	Titanium Dioxide (And) Aluminum Hydroxide (And) Triethoxycaprylylsilane	IR-Attenuation TiO ₂
New TiO2-IR300-11S2	Titanium Dioxide (And) Triethoxycaprylylsilane	



KPP-064G

Pressed Powder with CARESS® BN12

Part 1

- SERICITE GMS-4C - Kobo Products: Mica 70.48%
- BTD-11S2 - Kobo Products: Titanium Dioxide (And) Triethoxycaprylylsilane 7.00%
- MST-203 - Kobo Products: Polymethylsilsesquioxane 5.00%
- CARESS® BN12 - Bent Tree/Kobo Products: Boron Nitride 5.00%
- ZINC MYRISTATE - Kobo Products: Zinc Myristate 2.00%
- BYO-11S2 - Kobo Products: Iron Oxides (CI 77492) (And) Triethoxycaprylylsilane 1.00%
- BRO-11S2 - Kobo Products: Iron Oxides (CI 77491) (And) Triethoxycaprylylsilane 0.86%
- BBO-11S2 - Kobo Products: Iron Oxides (CI 77499) (And) Triethoxycaprylylsilane 0.46%
- Propyl Paraben NF - International Sourcing: Propylparaben 0.10%
- Methyl Paraben NF - International Sourcing: Methylparaben 0.10%

Part 2

- Lexol® PG-865 - Inolex Chemical Company: Propylene Glycol Dicaprylate/Dicaprate 2.50%
- ELEMENT14 PDMS 20 - Momentive: Dimethicone 2.50%
- ELEMENT14 PDMS 350 - Momentive: Dimethicone 2.00%
- SS4267 - Momentive: Dimethicone (And) Trimethylsiloxysilicate 1.00%

Manufacturing Procedure

1. Micropulverize Part 1 until color is fully developed.
2. Add Part 2 to Part 1.
3. Blend well.
4. Press at 500 psi.

Description

This powder features Kobo's CARESS® BN12, Boron Nitride, for superior softness and tactility, superb spreadability, excellent adherence, long lasting effect, and good coverage. SERICITE GMS-4C gives a glide-on application. The Silane-Treated Pigments disperse easily, adhere to the skin, and resist darkening during wear. MST-203 gives slip and a great creamy feel. ZINC MYRISTATE also contributes to great feel and adherence on the skin.

KOBO

Silane Treatment

www.koboproducts.com