



KEY-084A-EU

Sparkly Eyeshadow

%	INGREDIENT	INCI NAME	SUPPLIER
Part 1			
19.00	DUB PO	Ethylhexyl Palmitate	Stéarinerie-Dubois
10.00	DUN ININ	Isononyl Isononanoate	Stéarinerie-Dubois
7.50	SW55EB	Synthetic Wax (And) Iron Oxides (CI 77499) (And) Isopropyl Titanium Triisostearate	Kobo Products
4.00	KOBOGUARD® HRPC	Hydrogenated Polycyclopentadiene (And) Polyethylene (And) Copernicia Cerifera (Carnauba) Wax (And) Tocopherol	Kobo Products
3.00	Ozokerite Wax Pastilles SP-1021P	Ozokerite Wax	Strahl & Pitsch/Rossow
2.50	Performalene® 400	Polyethylene	New Phase
2.00	COSMOL™ 168ARV	Dipentaerythryl Hexahydroxystearate/Hexastearate/Hexarosinate	Ikeda
Part 2			
10.00	ASO-I2	Aluminum Starch Octenylsuccinate (And) Isopropyl Titanium Triisostearate	Kobo Products
5.00	DSPCS-I2	Silica (And) Ethylene/Methacrylate Copolymer (And) Isopropyl Titanium Triisostearate	Kobo Products
Part 3			
10.00	VegeLight 1214 LC	Coconut Alkanes (And) Coco-Caprylate/Caprates	Biosynthis
Part 4			
15.00	KTZ® SLATE	Titanium Dioxide (And) Mica (And) Iron Oxides (CI 77491) (And) Ferric Ferrocyanide	Kobo Products
12.00	KOBOPEARL® PERPETUAL LUSTER GreenBlue	Synthetic Fluorophlogopite (And) Silica (And) Titanium Dioxide	Kobo Products
100.00			

Description:

This Sparkly Eyeshadow features SW Pigmentary Dispersions that ease the manufacturing process. KOBOGUARD® HRPC is an oil resin that offers long wear. ASO-I2 offers a creamy feel and DSPCS-I2 provides a lightweight powdery application. Kobo's Pearlescent Pigments KTZ® SLATE and KOBOPEARL® PERPETUAL Luster GreenBlue give a unique colored sparkly effect.

Manufacturing Procedure:

1. Add Part 1 and heat to 85 °C while mixing until pigments are fully dispersed and waxes are completely melted.
2. Add Part 2 and mix until powders are fully incorporated.
3. Add Parts 3 and 4 and mix until homogeneous.



KOBO
www.koboproducts.com

November, 2017

FORMULATIONS

Product formulations are included as illustrative examples only. Kobo Products Inc. makes no representation or warranty concerning the efficacy or safety of any product manufactured using such formulations. All statements concerning the possible use of Kobo Products Inc. are for research purposes only. Responsibility for the performance or adequate testing of any product prior to sale or use of any such product lies with the manufacturer thereof.

USE OF PRODUCTS

Products sold by Kobo are designed, manufactured and sold for industrial use only. Prior to use of any such product for any application other than an industrial use, the user has the sole responsibility and obligation to determine the suitability of any such product for any such application.

PATENT STATUS

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

LIMITATION OF LIABILITY

Kobo Products Inc. shall in no event, whether the claim is based on warranty, contract, tort, strict liability, negligence or otherwise, be liable for incidental or consequential damages, or for any other damages in excess of the amount of the purchase price.

KOBO

The Powder & Dispersion Specialist



KOBO PRODUCTS, INC
3474 South Clinton Avenue
South Plainfield, NJ 07080
USA

Tel: +1 - 908 757 0033
Fax: +1 - 908 757 0905



KOBO BRASIL, LTDA
Rua Francisco Nakazato n. 2357
Itupeva SP 13.295-000
BRASIL

Tel: +55 (11) 5062 6034



KOBO PRODUCTS, LTD
67D(IV), Innovation Drive
Milton Park, Abingdon, OX14 4RQ
UNITED KINGDOM

Tel: +44 7913 636 673



KOBO PRODUCTS, SAS
135 Rue Buissonnière
Quartier Bouysset
31670 Labège
FRANCE

Tel: +33 - (0) 5 62 88 77 40
Fax: +33 - (0) 5 62 88 77 49



KOBO DISPATEK, INC
1-4-8 Nihombashi-bakurocho
Chuoko, Tokyo, 103-0002
JAPAN

Tel: +81 - 3 3663 8049
Fax: +81 - 3 3661 8679

www.koboproducts.com