



KEY-115B

Opalescent Silver Eyeshadow

%	INGREDIENT	INCI NAME	SUPPLIER
Part 1			
4.30	BBO-11S2	Iron Oxides (CI 77499) (And) Triethoxycaprylylsilane	Kobo Products
1.50	BRO-11S2	Iron Oxides (CI 77491) (And) Triethoxycaprylylsilane	Kobo Products
0.20	BYO-11S2	Iron Oxides (CI 77492) (And) Triethoxycaprylylsilane	Kobo Products
Part 2			
35.00	KTZ® SUPERB SILVER-11S2	Mica (And) Titanium Dioxide (And) Triethoxycaprylylsilane	Kobo Products
15.00	KTZ® SLATE-11S2	Titanium Dioxide (And) Mica (And) Iron Oxides (CI 77491) (And) Ferric Ferrocyanide (And) Triethoxycaprylylsilane	Kobo Products
5.00	KTZ® MISTERIOSO BLUE-11S2	Mica (And) Titanium Dioxide (And) Iron Oxides (CI 77499) (And) Triethoxycaprylylsilane	Kobo Products
2.50	KTZ® SM CRYSTAL WHITE	Synthetic Fluorophlogopite (And) Titanium Dioxide (And) Silica	Kobo Products
2.50	KTZ® G QUARTZ	Calcium Sodium Borosilicate (And) Titanium Dioxide	Kobo Products
2.00	MSS-500W	Silica	Kobo Products
Part 3			
1.00	ZINC STEARATE	Zinc Stearate	Soda Nikka Co., Ltd.-JPY
1.00	Lexgard® O	Caprylyl Glycol	Inolex
Part 4			
13.20	KOBOGUARD® 50AMP-G	Acrylates/Ethylhexyl Acrylate Copolymer (And) Water (And) Aminomethyl Propanol	Kobo Products
Part 5			
11.85	Neosolue™-DiSM	Diisostearyl Malate	Nippon/Kobo Products
3.00	Xiameter® PMX-200 Silicone Fluid 5CS	Dimethicone	Dow Chemical
1.80	Lanette® 22	Behenyl Alcohol	BASF
0.15	Monomuls® 90-O 18	Glyceryl Oleate	BASF
100.00			

Description:

This precious light eyeshadow blends beautifully and adds instant glam by providing a clean metallic foil look with stunning luster. Kobo's Silane (11S) treatment helps to provide this pressed powder with adhesion to the skin and gives the formula a creamy feel. The combination of KTZ® SUPERB SILVER-11S2 and KTZ® G QUARTZ provides a silver chrome effect to the formula. Silane Treated KTZ® SLATE-11S2 provides a teal color and pearlescent effect. Silane Treated KTZ® MISTERIOSO BLUE-11S2 imparts a unique color effect. KTZ® SM CRYSTAL WHITE imparts a shimmering-on-foil visual effect. MSS-500W gives slip and a great creamy feel. KOBOGUARD® 50AMP-G helps form a flexible film that improves wear. Neosolue™-DiSM contributes to the smooth texture and emolliency of the formula.

Manufacturing Procedure:

1. Micropulverize Part 1 until uniform. □
2. Add Part 2 to Part 1. Micropulverize at low speed. □
3. Pre-mix ingredients of Part 3. Mix together until uniform. □
4. Combine Part 5. Prop mix until uniform while heating to 80° C.
5. Cool Part 5 to RT by mixing under prop.
7. Slowly add Part 4 to Part 5 @ 50° C until homogeneous. □
8. Add Parts 4 and 5 emulsion to main batch through □ micropulverization until bulk looks homogeneous. □
9. Press at 100 psi.



KOBO
www.koboproducts.com

October, 2020

FORMULATIONS

Product formulations are included as illustrative examples only. Kobo Products Inc. makes no representation or warranty concerning the efficacy or safety of any product manufactured using such formulations. All statements concerning the possible use of Kobo Products Inc. are for research purposes only. Responsibility for the performance or adequate testing of any product prior to sale or use of any such product lies with the manufacturer thereof.

USE OF PRODUCTS

Products sold by Kobo are designed, manufactured and sold for industrial use only. Prior to use of any such product for any application other than an industrial use, the user has the sole responsibility and obligation to determine the suitability of any such product for any such application.

PATENT STATUS

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

LIMITATION OF LIABILITY

Kobo Products Inc. shall in no event, whether the claim is based on warranty, contract, tort, strict liability, negligence or otherwise, be liable for incidental or consequential damages, or for any other damages in excess of the amount of the purchase price.

KOBO

The Powder & Dispersion Specialist



KOBO PRODUCTS, INC
3474 South Clinton Avenue
South Plainfield, NJ 07080
USA

Tel: +1 - 908 757 0033
Fax: +1 - 908 757 0905



KOBO BRASIL, LTDA
Rua Francisco Nakazato n. 2357
Itupeva SP 13.295-000
BRASIL

Tel: +55 (11) 5062 6034



KOBO PRODUCTS, LTD
67D(IV), Innovation Drive
Milton Park, Abingdon, OX14 4RQ
UNITED KINGDOM

Tel: +44 7913 636 673



KOBO PRODUCTS, SAS
135 Rue Buissonnière
Quartier Bouysset
31670 Labège
FRANCE

Tel: +33 - (0) 5 62 88 77 40
Fax: +33 - (0) 5 62 88 77 49



KOBO DISPATEK, INC
1-4-8 Nihombashi-bakurocho
Chuoko, Tokyo, 103-0002
JAPAN

Tel: +81 - 3 3663 8049
Fax: +81 - 3 3661 8679

www.koboproducts.com

www.koboproducts.com