



KPP-105B-BR

Super Creamy Pressed Powder

%	INGREDIENT	INCI NAME	SUPPLIER
Part 1			
85.30	TALC AJM	Talc	Kobo Products
3.00	BTD-401	Titanium Dioxide (And) Isopropyl Titanium Triisostearate	Kobo Products
2.00	CARESS® BN06	Boron Nitride	Bent Tree/Kobo Products
2.00	BYO-I2	Iron Oxides (CI 77492) (And) Isopropyl Titanium Triisostearate	Kobo Products
1.50	ZINC MYRISTATE (MB)	Zinc Myristate	Kobo Products
0.66	BRO-I2	Iron Oxides (CI 77491) (And) Isopropyl Titanium Triisostearate	Kobo Products
0.34	BBO-I2	Iron Oxides (CI 77499) (And) Isopropyl Titanium Triisostearate	Kobo Products
0.10	Propilparabeno	Propylparaben	Cosmotec
0.10	Metilparabeno	Metylparaben	Cosmotec
Part 2			
3.50	SALACOS® P-8	Ethylhexyl Palmitate	Ikeda/Kobo Products
1.50	Xiameter PMX-200 Silicone Fluid 50CS	Dimethicone	Dow Corning
100.00			

Description:

This is an economical pressed powder. It features ITT treated pigments and Mica that give great feel and adherence on the skin. TALC AJM is an odorless, fine, white powder with anti-caking properties to improve feel. ZINC MYRISTATE (MB) works as a dry binder due to its good pressability. SALACOS® P-8 acts as a liquid binder and helps to achieve an enhanced feel. CARESS® BN06 gives a creamy and luxurious feel.

Manufacturing Procedure:

1. Blend Part 1 until the pigments are fully dispersed
2. Add Part 2 drop by drop and mix well until the binders are dispersed.
3. Pass the bulk through the sieve 2 times.
4. Press at 500psi.



KOBO
www.koboproducts.com

December, 2021

FORMULATIONS

Product formulations are included as illustrative examples only. Kobo Products Inc. makes no representation or warranty concerning the efficacy or safety of any product manufactured using such formulations. All statements concerning the possible use of Kobo Products Inc. are for research purposes only. Responsibility for the performance or adequate testing of any product prior to sale or use of any such product lies with the manufacturer thereof.

USE OF PRODUCTS

Products sold by Kobo are designed, manufactured and sold for industrial use only. Prior to use of any such product for any application other than an industrial use, the user has the sole responsibility and obligation to determine the suitability of any such product for any such application.

PATENT STATUS

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

LIMITATION OF LIABILITY

Kobo Products Inc. shall in no event, whether the claim is based on warranty, contract, tort, strict liability, negligence or otherwise, be liable for incidental or consequential damages, or for any other damages in excess of the amount of the purchase price.

KOBO

The Powder & Dispersion Specialist



KOBO PRODUCTS, INC
3474 South Clinton Avenue
South Plainfield, NJ 07080
USA

Tel: +1 - 908 757 0033
Fax: +1 - 908 757 0905



KOBO BRASIL, LTDA
Rua Francisco Nakazato n. 2357
Itupeva SP 13.295-000
BRASIL

Tel: +55 (11) 5062 6034



KOBO PRODUCTS, LTD
67D(IV), Innovation Drive
Milton Park, Abingdon, OX14 4RQ
UNITED KINGDOM

Tel: +44 7913 636 673



KOBO PRODUCTS, SAS
135 Rue Buissonnière
Quartier Bouysset
31670 Labège
FRANCE

Tel: +33 - (0) 5 62 88 77 40
Fax: +33 - (0) 5 62 88 77 49



KOBO DISPATEK, INC
1-4-8 Nihombashi-bakurocho
Chuoko, Tokyo, 103-0002
JAPAN

Tel: +81 - 3 3663 8049
Fax: +81 - 3 3661 8679

www.koboproducts.com

www.koboproducts.com